



THERMATEX® Laguna micro

THERMATEX® ceiling tiles are made of modern, bio-soluble mineral wool, perlite, clay and starch with excellent outstanding physical properties in fire resistance and acoustic performance.




SYSTEM	■ Exposed Grid System, demountable ceiling
Dimensions	■ 600 x 600 mm, 625 x 625 mm, plank sizes up to 2500 mm available
Thickness / Weight	■ 15 mm (c. 4.0 kg/m ²)
Colour	■ White similar to RAL 9010
Edge details	■ SK, VT 15/24



TECHNICAL PERFORMANCE

Reaction to fire	■ A2-s1, d0 as per EN 13501-1
Fire protection	■ Up to 60 minutes as per BS 476: parts 20 - 23 (according to test certificate)
Sound absorption	■ EN ISO 354 $\alpha_w = 0.60$ as per EN ISO 11654 $NRC = 0.60$ as per ASTM C 423
Sound attenuation	■ $D_{n,f,w} = 34$ dB as per EN ISO 10848 (15 mm thickness, according to test certificate)
Light reflectance	■ Up to 88%
Thermal conductivity	■ $\lambda = 0.052 - 0.057$ W/mK as per DIN 52612
Humidity	■ Up to 90% RH



Due to reproduction processes colours shown in this catalogue may differ from the actual product colour. Product selection should always be made from AMF samples. All details and technical information stated in this brochure or other publicity material referring to AMF ceiling systems are based on test reports obtained under laboratory conditions. It is the responsibility of the customer to ensure that this data is suitable for the proposed application. All information provided is based on current technical data. Further relevant test reports, assessments and installation guidelines are available. All system details conform with current standards and are based on the use of AMF products and system components. AMF accepts no liability or responsibility for use of third party components, or for any variations to conditions stipulated in test data. Mixing of production batches is not recommended. All technical data is subject to change without prior notice and is governed by AMF Terms and Conditions of Sales. This catalogue supersedes all previous editions. Errors and omissions excepted. Printing errors excepted.



Knauf AMF GmbH & Co. KG
Elsenthal 15
D-94481 Grafenau Germany
Telefon 08552 / 422-0 - Fax 08552 / 422-32
info@knaufamf.de - www.knaufamf.com